

ers • Deck Coatings • Waterproofing Systems • Hot Applied Membranes • Liquid Membranes • S  
ied Membranes • Sheet Membranes • Butyl Membranes • Drainage Systems • Roofing Underlayment  
or & Air Barriers • Deck Coatings • Waterproofing Systems • Hot Applied Membranes • Liquid Membranes • S  
ray Applied Membranes • Sheet Membranes • Butyl Membranes • Drainage Systems • Ro  
erlayment • Vapor & Air Barriers • Deck Coatings • Waterproofing Systems • Hot Applied Membranes • Liquid Membranes • S  
id Membranes • Spray Applied Membranes • Sheet Membranes • Butyl Membranes • Drainage Systems

**CCW-525**

**Liquid Applied Waterproofing Membrane**

C A R L I S L E C O A T I N G S & W A T E R P R O O F I N G



800.527.7092 | [www.carlisle-ccw.com](http://www.carlisle-ccw.com)

**CARLISLE**  
Coatings & Waterproofing



# CCW-525 Liquid Applied Waterproofing Membrane

Carlisle Coatings & Waterproofing, Inc. (CCW) provides a broad range of solutions to meet specific waterproofing needs. CCW offers technical services, research & development and manufacturing capabilities from its headquarters in Wylie, Texas and three additional manufacturing facilities in Terrell, TX, Elberton, GA, and Carlisle, PA. The CCW network is further supported by over 50 manufacturer's sales representatives directed by regional sales offices throughout the country. CCW offers a complete line of waterproofing and moisture protection products for the architectural, general construction, industrial and maintenance industries. Carlisle Coatings & Waterproofing, Inc., is part of the SynTec Division of Carlisle Companies, Inc., which is a publicly traded company on the NYSE.

CCW-525 is the simple solution for waterproofing difficult below grade areas with penetrations or various angle changes. This one-part, cold applied liquid material cures to form a monolithic membrane providing lasting waterproofing protection. CCW-525 compliments other Carlisle Waterproofing systems by detailing critical areas such as transitions and angle changes, while its single-person, one-step application allows for improved jobsite efficiency.

CCW-525's moisture cured, modified polyurethane properties cure to form a strong, flexible membrane for various below grade applications. With an available

reinforced system for heavy-duty applications, CCW-525 may be layered for greater strength and protection. It provides tenacious adhesion to concrete substrates preventing lateral water migration for both vertical and horizontal surfaces. CCW-525's performance is enhanced when combined with the appropriate CCW MiraDRAIN drainage system. CCW MiraDRAIN protects the waterproofing membrane, provides a channel for proper water migration and eliminates hydrostatic pressure. The inherent toughness and resilience of the CCW-525 membrane enables it to bridge structural or shrinkage cracks, which may develop in the substrate, providing lasting waterproofing protection.

## TYPICAL USES

CCW-525 is available in three viscosities (H, R & V) for application to horizontal and vertical surfaces. Typical applications are between structural slabs, parking garages, plaza decks, balconies, roof decks, terraces and mechanical equipment rooms. CCW-525 is ideally suited for waterproofing on below grade foundation walls, tunnels, planters and other areas where seamless, elastomeric waterproofing is required.

## STANDARD, TESTS, CERTIFICATES

- ASTM Specification: ASTM C 836-95

## PACKAGING, TYPES & ACCESSORIES

- 5 gallon pails and 55 gallon drums
- CCW-525-H – Horizontal Grade (self leveling)
- CCW-525-R – Roller Grade
- CCW-525-V – Vertical Grade (roller applied)
- Carlisle DCH Polyester Reinforcing Fabric – 40" x 324'
- CCW-201 Mastic – 1.5 Gallon Kit
- CCW-557 Epoxy Primer – 4 & 10 Gallon Kits
- CCW-559 Metal Primer – 2 Quart Kits

## INSTALLATION

**Surface Preparation:** New concrete shall be water cured, followed by a light hair broom, trowel finish and in place for 14 days minimum, 28 days preferred. If curing compounds are required, use the self dissipating type or as approved by Carlisle. CCW-525 adheres to surfaces that are structurally



sound, dry, and free of oil, grease, dirt, laitance, curing or release agents and other contamination which may harmfully affect the adhesion of the membrane. Block wall mortar joints must be struck flush.

Remove splatters, fins, ridges or other projections to provide a smooth, level surface. Fill tie rod holes, honeycombs, rock pockets, spalls or other voids and indentations with non-shrink grout.

Saw cut moving cracks greater than 1/16" in width to 1/4" wide by 1/4" deep. Provide a smooth and level surface by grinding or filling (as required) the surface at cold joints where each pour is at a different plane. Clean metal to expose a bright finish.

For detail work, clean joints and saw-cut cracks per the dimensions provided above. All moving cracks over 1/16" wide and all expansion joints less than 1" wide shall be cleaned, primed, fitted with a backing rod and caulked with Carlisle Polyurethane Sealant as recommended by the data sheet. For larger joints, contact a Carlisle representative.

Apply a 1", 45 degree angle sealant cant of CCW-201 at the juncture of all vertical and horizontal surfaces including around pipes, vents and other projections. Apply bond-breaker tape (or wax) over the sealant installed in expansion joints and saw cut cracks. When using bondbreaker tape, apply three times the width of the joint.

Apply a 4" to 6" wide stripe coat of CCW-525-V over all sealed cracks, joints and over all hairline cracks and cold joints. Apply a stripe coat of CCW-525-V over sealant cants and up the vertical wall to the height referred to on the applicable detail drawing, (minimum 8" recommended) and onto the horizontal deck 4" to 6". Apply stripe coat at 45 ± 5 mils and allow to cure overnight.



## FEATURES AND BENEFITS

- Liquid-Applied Membrane
- Single Component
- Moisture Cured
- Coal-Tar Free
- Cures to an Elastomeric, Monolithic Membrane
- Vertical or Horizontal Application
- Provides Tenacious Adhesion
- Perfect for Planters
- Can be used on Smaller Areas & Detail Work

**Priming:** For adhesion to dry, nonporous-concrete, primer is not necessary. However, if pinhole and blister problems occur as a result of air and/or moisture vapors emitted from the concrete and environmental conditions, it is recommended that the surface be primed with CCW-557 primer. For metal surfaces, apply CCW-559 primer immediately after sanding and cleaning.

Primer must be allowed to stand for 15 minutes after mixing. Allow primer to cure for 1 hour minimum. Primer is sufficiently cured when it will not transfer when touched. In the event primed surface becomes dirty, reprime. Prime only an area that can be covered in one day. Refer to the CCW-557 and CCW-559 data sheets for information regarding its specific usage.

For metal surfaces, apply CCW-559 primer immediately after sanding and cleaning. Primer must be allowed to stand for 15

minutes after mixing. Allow primer to cure for one hour minimum. Primer is sufficiently cured when it will not transfer when touched. In the event primed surface becomes dirty, reprime. Prime only an area that can be covered in one day.

**Application:** Prior to detail work, wipe all areas with a clean cloth containing xylene solvent and allow the prepared area to dry.

*Horizontal:* Apply CCW-525-H over the cleaned, primed flange of drains, taking care not to fill weep holes. Using a notched squeegee, apply CCW-525-H at 25 sq. ft. per gallon or as required to obtain a 60 mil thickness, to the entire area, including over all detail coats.

*Vertical:* Using a medium nap roller, apply CCW-525-V or CCW-525-R in two coats at a rate of 50 sq. ft. per gallon or as required to obtain 30 mils per coat for a total thickness of 60 mils.

*Reinforced System:* Apply CCW-525-H at 25 sq. ft. per gallon or as required to obtain a 60 mil thickness to the entire area, including over all detail coats.

Use a 1/4" notched squeegee or flat squeegee with guide pins to achieve a uniform thickness. Immediately install Carlisle DCH white polyester reinforcing fabric. Install carefully to avoid wrinkles. In the event of wrinkles or fishmouths, cut the fabric and overlap the excess to avoid trapped air. Extend the second layer of CCW-525 past the edge of the fabric to completely encapsulate the first layer. The completed system will be a total of 120 mils thick.



**Protection:** The membrane must be protected from damage by future operations and other trades. CCW Protection Board is recommended for both vertical or horizontal surfaces. Install a protection course on vertical walls immediately after membrane has cured (36 hrs. at 75°F). Install the protection course on horizontal application immediately following successful flood testing. If flood test is delayed, install a temporary covering to protect the membrane from other trades.

**Flood Test:** After membrane has cured 36 to 72 hours, plug drains and provide necessary barriers to contain flood water. Flood deck with a 1" head of water and allow to stand for 24 hours. Check for leaks and immediately make repairs if required. Retest after any repairs have been made.

**Clean Up:** Before material cures, clean adjacent areas to remove stains or spills and clean tools with toluene or xylene. **Do not clean or wash skin with solvents.**



### TECHNICAL DATA

Property	Application Type	Test Method	Results*
Composition	Horizontal, Vertical & Roller	—	Modified Polyurethane
Color	Horizontal, Vertical & Roller	—	Black
Tack Free Time	Horizontal, Vertical & Roller	@ 75°F (24°C), 50% RH.	16 hours
Cure Time	Horizontal, Vertical & Roller	@ 75°F (24°C), 50% RH.	36 hours
Solids Content	Horizontal, Vertical & Roller	ASTM D 2369	82% (+/- 2)
Hardness	Horizontal, Vertical & Roller	ASTM D 2240	30 Shore A (min.)
Elongation	Horizontal	ASTM D 412	575%
	Vertical & Roller	ASTM D 412	600%
Tensile	Horizontal	ASTM D 412	250 psi
	Vertical & Roller	ASTM D 412	400 psi
Permeability	Horizontal	ASTM E 96	0.07384 perms
	Vertical & Roller	ASTM E 96	0.07176 perms
Adhesion to Primed Concrete	Horizontal	ASTM D 903	14.9 lbs/in (12.9kg/cm)
	Vertical & Roller	ASTM D 903	19.0 lbs/in (16.4kg/cm)

\* Individual lots may vary +/- 10% from Typical value

## COMPLETE WATERPROOFING ONE COMPANY

CCW provides a complete line of waterproofing solutions and the expertise to help you select the one that is best for your project.



CCW Deck Coatings



ECO-FAST Deck Coating System



CCW-500R



Barricoat-S




CCW MiraDRI 860/861



CCW MiraCLAY



CCW MiraDRAIN



CCW WIP



Vapor/Air Barrier Systems

## CCW WEB

Visit Our Web Site at

[www.carlisle-ccw.com](http://www.carlisle-ccw.com)

- Updates
- Data Sheets
- Contacts
- Guide Specifications
- Architectural Details
- Technical Bulletins

## LIMITED WARRANTY

CARLISLE COATINGS & WATERPROOFING, INCORPORATED (CARLISLE) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any CARLISLE materials prove to contain manufacturing defects that substantially effect their performance, CARLISLE will, at its option, replace the materials or refund its purchase price.

This limited warranty is the only warranty extended by CARLISLE with respect to its materials. There are no other warranties including the implied warranties of merchantability and fitness for a particular purpose.

CARLISLE specifically disclaims liability for any incidental, consequential or other damages including, but not limited to, loss of profits or damages to a structure or its contents arising under any theory of law whatsoever.

The dollar value of CARLISLE's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the CARLISLE material in question.

**Carlisle Coatings & Waterproofing, Incorporated**  
 900 Hensley Lane, Wylie TX 75098  
 800.527.7092 • [www.carlisle-ccw.com](http://www.carlisle-ccw.com)

