



DECK-THANE PRIMER

SINGLE COMPONENT VOC COMPLIANT MOISTURE CURED PRIMER

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION:

Pacific Polymers® DECK-THANE Primer is a single component, moisture cured, solvent-borne, VOC compliant polyurethane primer for concrete and wood surfaces.

BASIC USES: Used to promote adhesion of ELASTO-DECK 5000 polyurethane deck coating systems, Joint Sealants and Elasto-Deck BT and Elasto-Mat series to Concrete and Wood. Also used to achieve adhesion between coats of Elasto-Deck BT, Elasto-Deck BT H20 and Elasto-Mat D&G.

COLOR: Amber yellowish liquid.

PACKAGING: 1 gallon cans, and 5 gallon pails.

LIMITATIONS: All materials shall be delivered to the job site in unopened containers clearly marked and labeled. Containers that have been opened must be used up within one or two days since it is a moisture-reactive material. The material will cure when exposed to air. All surfaces must be completely free of foreign matter and primed, where necessary.

WARNINGS AND HAZARDS:

Before using the products, always refer to MSDS for important warnings and safety information. Use only in areas with adequate ventilation. Avoid breathing vapors. Keep away from heat and flame. Avoid contact with eyes and skin. In the event of skin contact, remove immediately and wash with warm, soapy water. Wear suitable eye protection. Always wash hands before eating.

INSTALLATION:

- All surfaces which are to be coated with DECKTHANE PRIMER must be free of contamination such as curing compounds, concrete hardeners, bond breakers, paint, etc. We recommend water-curing concrete instead of using concrete curing compounds. All surfaces must be clean, sound and dry. Sandblasting is recommended when possible, otherwise acid etching and wire-brushing may be sufficient.
- **Coverage:** 250 to 350 sq.ft. per gallon depending on the surface. Rough surfaces may require 250 sq.ft per gallon, smoother surface may require up to 350 sq.ft. per gallon.
- All solvents must be allowed to evaporate off before application over **DECK-THANE PRIMER** is possible. For best results, the surface that has been coated with **DECK-THANE PRIMER** should be allowed to cure for a minimum of 2 hours before the application of the polyurethane membrane or joint sealant. If for some reason the primer is allowed to cure in excess of 8 hours, the surface should be sanded and re-primed with **DECK-THANE PRIMER**.
- **DECK-THANE PRIMER** should not be applied over wet surfaces as full adhesion and penetration will not be obtained. **DECK-THANE PRIMER** may be applied by brush, roller or spray. Containers that have been opened must be used up within one or two days since it is a moisture-sensitive product.

- **Clean Up:** Because of the difficulty in cleaning up or removing cured **DECK-THANE PRIMER**, equipment and tools should be cleaned immediately after use with acetone or other exempt solvent.

AVAILABILITY AND COST:

- **DECK-THANE PRIMER** is supplied through building material dealers. Prices vary with quantity and packaging. Quotations are made upon request.
- These products are designed and manufactured to be installed by professional installers familiar with surface preparation and application procedures. All others should consult a professional installer; those who choose to install these products without professional assistance do so at their own risk.

PRODUCT WARRANTY:

SATISFACTORY RESULTS DEPEND NOT ONLY UPON QUALITY PRODUCTS BUT ALSO UPON FACTORS BEYOND OUR CONTROL; METHODS OF APPLICATION AND SITE CONDITIONS ARE EXAMPLES OF SUCH FACTORS AND CAN AFFECT PRODUCT PERFORMANCE. THIS WARRANTY CONSEQUENTLY EXTENDS ONLY TO PRODUCTS INSTALLED IN STRICT ACCORDANCE WITH THE MANUFACTURER'S SPECIFICATIONS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF, BY HIS OWN INFORMATION AND TESTS, OF THE SUITABILITY OF THE PRODUCT FOR HIS OWN INTENDED USE; USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM HIS USE OF THE PRODUCT. THE SUBSTRATE TO WHICH THE PRODUCT IS APPLIED MUST BE SOUND STRUCTURALLY AND OTHERWISE. STRUCTURAL OR SUBSTRATE FAILURES OR IMPERFECTIONS RESULTING IN DAMAGE TO OR FAILURE OF THE PRODUCT ARE NOT COVERED BY THIS WARRANTY.

SINCE THE USE OF THE PRODUCT IS BEYOND THE CONTROL OF THE MANUFACTURER, THE MANUFACTURER ASSUMES NO LIABILITY FOR MISAPPLICATION AND MISUSE OF THE PRODUCT.

THIS WARRANTY DOES NOT COVER CONSEQUENTIAL DAMAGES, NOR DOES IT COVER THE LABOR ATTENDANT TO REPLACING PRODUCT IN THE EVENT OF A PRODUCT FAILURE. THE WARRANTY ONLY EXTENDS TO REPLACEMENT OF THE PRODUCT ITSELF.

ALL PRODUCTS PROVEN TO BE DEFECTIVE IN MANUFACTURE WILL BE REPLACED AT NO CHARGE. SINCE THE USE OF THESE PRODUCTS IS BEYOND OUR CONTROL WE CANNOT ASSUME ANY RISK OR LIABILITY FOR RESULTS OBTAINED, NOR CAN WE ACCEPT DAMAGES IN EXCESS OF THE PURCHASE PRICE OF THESE PRODUCTS.

Complete technical information is available from
ITW Polymers Sealants North America, Inc.

ITW POLYMERS SEALANTS NORTH AMERICA, INC.

111 S. Nursery Road. Irving, TX 75060

Tel: 972-438-9111 Fax: 972-554-3939 www.itwsealants.com

4/28/2014

TECHNICAL SERVICE

All of the latest updates to product data and specifications are available at www.pacpoly.com. Since product data and specifications change, it is the user's responsibility to make certain the most current versions of product data and specifications are being used.

Technical assistance can be obtained by contacting:

ITW POLYMER SEALANTS NORTH AMERICA

12271 Monarch Street
Garden Grove, CA 92841
Tel: 1-800-888-8340
Fax: 714-898-5687

TECHNICAL DATA

Property	Typical Results
Consistency	Fluid
Color	Yellowish to amber
Odor	Mild aromatic odor
Weight Per Gallon	9.55 +/- 1.10 pounds (@75°F)
Viscosity (Brookfield)	500 maximum cps (@75°F)
Dry to touch	2 hours (@ 75°F, 50% RH min)
Solid Content	68% +/- 2% (Weight)
VOC Content	98 g/l (Minus exempt solvent)
Shelf Life	6 months minimum (unopened containers stored in cool dry locations)
Cure Time	Minimum 2 hours, 8 hours maximum